



## Architectural Colors

### Paint Specifications

COLOR	REFLECTANCE	EMISSIVITY	SRI
ALMOND	0.60	0.84	70
ASH GRAY	0.39	0.84	41
BONE WHITE	0.71	0.85	86
BRANDYWINE	0.26	0.85	24
BRITE RED	0.42	0.84	45
BUCKSKIN	0.38	0.86	41
CHAMPAGNE METALLIC	0.38	0.80	38
CHARCOAL	0.32	0.85	32
COLONIAL RED	0.33	0.85	34
COPPER PENNY	0.49	0.85	55
DARK BRONZE	0.26	0.84	24
EVERGREEN	0.26	0.84	24
*GALVALUME PLUS	0.69	0.19	62
HARTFORD GREEN	0.25	0.85	23
LEADCOAT	0.37	0.82	38
MANSARD BROWN	0.30	0.85	30
MATTE BLACK	0.27	0.86	26
MEDIUM BRONZE	0.30	0.87	31
PATINA GREEN	0.46	0.85	51
PATRICIAN BRONZE	0.27	0.86	26
PREWEATHERED GALVALUME	0.30	0.79	27
REGAL BLUE	0.26	0.85	24
REGAL WHITE	0.68	0.86	82
ROMAN BLUE	0.26	0.85	24
SANDSTONE	0.54	0.86	63
SILVER METALLIC	0.57	0.78	64
SLATE GRAY	0.43	0.85	47
SURREY BEIGE	0.40	0.86	43
TERRA COTTA	0.35	0.85	36
TEXAS SILVER METALLIC	0.58	0.78	66

\*Bare Acrylic Coated Galvalume

#### Notes:

- Solar Reflectance is a measure of the amount of solar energy that is immediately reflected from the surface.
- Solar Emissivity is the ability of a material to emit the residual heat back into the surrounding atmosphere.
- The Solar Reflectance Index (SRI) is a measure of the roof's ability to reject solar heat, considering reflectance, emissivity and convection across the surface.

#### General Notes:

- Inventory and color offering can change without notice. Please contact your McElroy representative to confirm availability.
- Other widths and gauges are available on some items.
- Galvalume® is McElroy's standard substrate. G90 is available upon request.
- McElroy Metal features Fluoropon® PVDF coatings on all products.
- Fluoropon is manufactured by Sherwin-Williams Corporation.



CORPORATE OFFICE

1500 HAMILTON RD. • BOSSIER CITY, LA 71111